




## Ruote di comando e rulli di rinvio per maglia codice 14218 Drive sprockets and driven wheels for links code 14218

Chain-Forged Links  
**GEAR-WHEELS**



Codice/Code	Dimensioni / Dimensions							Peso al metro Weight per meter
	P	T	C	S	F	R	D	Kg/m
14218	142	42	50	19	20	11	25	9,40

Materiali Materials	MN 18MnCrB5	CN 18NiCrMo5	C40 C45	CD 42CrMo4
Trattamento termico Heat treatment	Cementazione temprata Case hardening	Cementazione temprata Case hardening	Bonifica Hardening and tempering	Bonifica Hardening and tempering
Carico di rottura medio teorico (kN) Average theoretical breaking load (kN)	290	320	370	550

### ► Rullo di rinvio / Driven-wheel

Codice/Code	Dimensioni / Dimensions			
	De	Di	Df	S
14218/06R	234	210	40	50
14218/07R	280	256	40	50
14218/08R	320	296	40	50
14218/09R	362	338	40	50
14218/10R	415	391	40	50
14218/11R	454	430	40	50
14218/12R	500	476	40	50
14218/13R	545	521	40	50
14218/14R	588	564	40	50
14218/15R	632	608	40	50
14218/16R	677	653	40	50

